



IRAN KETONE Sealer (water-base)

Test Specifications	Result
Nonvolatile content	43 ± 1 %
Viscosity at(25°C)	100-120 (cp)
Acidity (PH)	6-9
Acid value	30 (mg KOH / gr)
Curation time at (25°C)	8 hr
Tough free time	20-30 min
Water absorption after full curing	3-6 %
Specific weight	1.01(gr/ml)
Appearance	Milkly white

Applications:

Staining of interior wooden furniture, panels, door, window. wooden decorative (interior & exterior) coating, refinish for furniture, Conventional spray coating, dipping, roller coating.

Principle properties:

Water base sealer is environment friendly product with good human health, spray able on wooden surface with water absorption & moisture resistance, hardening of wooden texture with glossiness properties, good sand ability, UV and weathering resistance.

- Very good hardness
- Without yellowing
- Quick dry time
- Good stability

Storage:

- Keep away from sources of ignition, heat and sun light.
- Stored between 10°C to 25°C .
- Keep away from children, do not take orally.
- Please after use close the container door.

Shelf life:

This product has a shelf life of 6 months from data.

Note: the information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use.



Apply procedure:

First clean the wood surface and then shake the sealer container and filtered the resin, for better spray ability can use from air assist pistollet with nuzzle(1.3 – 1.5 inch) at 1 bar presser without adding water.

Note:

- Spray on the wooden surface and repeat if need.
- For sealing the inaccessible area with pistollet can use brush the sealer to surface.
- After finished the coating wash the pistollet with distillated water.

Drying condition at 25 °C	
Tough free (surface drying)	10-20 min
Full curing	6-8 hr
Handel and transfer	After 8 hr