IRAN KETONE COMPANY GROUP

The first manufacturer of polyester resins Since 1975 in IRAN



IRAN KETONE AC 227

Acrylic Polyol resin (high solid)

Test Specifications		Result
Solid Content	(ASTM D-1259)	65±1%
Acid Value	(ASTM D-1639)	4-6 (mg KOH/gr)
Hydroxyl content (on solid)(ASTM D-4274)		2.7 ± 0.1 %
Density (25°C)	(ASTM D-1475)	1.14 (gr / ml)
Viscosity (25°C)(delivery form)(ASTM D-562)		5000-6000 (cp)
Color, Gardner	(ASTM D-1544)	1-2
Solvent		Xylene
Flash Point (ASTM D-93)		24 (°C)
Compatible Solvent		Glycol ethers, aromatic hydrocarbons, esters, ketones
Partial compatible solvent		Some alcohols, some aliphatic hydrocarbons.
Other resin & hardener compatibility		Aliphatic & aromatic polyisocyanat, melamine & urea, aerylic polyol series IK200.
Curation/ drying mechanism		Solvent evaporation / chemical reaction

Applications:

- Wood coating.
- Automotive refinish paint (Economy grade for PU coatings).
- Transportations & industrial polyurethane anti-corrosive coatings.
- High solid polyurethane paint and clear(auto lacquer).

Principle properties:

- Good adhesion to metal & plastic surface.
- Fast drying and good distinctness of image (DOI).
- Good chemical, weathering and UV resistance.
- Good pigment wetting.

Storage:

- Keep away from sources of ignition and heat.
- Stored between 0°C to 40°C.

Shelf life:

• This product has a shelf life of 12 months from data of manufacture.

Note: the information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use.

No8, ghanee rad St, South Shiraz St, Mollasadra St, Vanak Sq, Tehran, Iran. www.IRANKETONE.com – info@iranketone.com

Tell-Fax: +98-21-88059405-8





